

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/01-CPR-13-1

- 1) Code of the product type: **1.0038**
2) Type: **Sections/Bars S235JR according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	235		
	16	40	225		
	40	63	215		
	63	80			
	80	100			
	100	140	195		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	360	510	
	100	140	350	500	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	26		
	40	63	25		
	63	100	24		
100	140	22			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at +20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,35		
	30	40	0,35		
40	140	0,38			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,17	Cu : 0,55	
			Mn : 1,40	S : 0,040	
			P : 0,040	N** : 0,012	
	* For nominal thickness > 40 mm C: 0,20. For nominal thickness >100 mm: C content upon agreement				
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/02-CPR-13-1

- 1) Code of the product type: **1.0114**
2) Type: **Sections/Bars S235J0 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	235		
	16	40	225		
	40	63	215		
	63	80			
	80	100			
	100	140	195		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	360	510	
	100	140	350	500	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	26		
	40	63	25		
	63	100	24		
	100	140	22		
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at 0°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,35		
	30	40	0,35		
	40	140	0,38		
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,17	Cu : 0,55	
			Mn : 1,40	S : 0,035	
			P : 0,035	N** : 0,012	
	* For nominal thickness >100 mm: C content upon agreement.				
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/03-CPR-13-1

- 1) Code of the product type: **1.0117**
2) Type: **Sections/Bars S235J2 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	235		
	16	40	225		
	40	63	215		
	63	80			
	80	100			
100	140	195			
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	360	510	
	100	140	350	500	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	26		
	40	63	25		
	63	100	24		
100	140	22			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at -20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,35		
	30	40	0,35		
40	140	0,38			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,17	Cu : 0,55	
			Mn : 1,40	S : 0,030	
			P : 0,030		
* For nominal thickness >100 mm: C content upon agreement. Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)					

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/04-CPR-13-1

- 1) Code of the product type: **1.0044**
2) Type: **Sections/Bars S275JR according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	275		
	16	40	265		
	40	63	255		
	63	80	245		
	80	100	235		
	100	140	225		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	410	560	
	100	140	400	540	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	23		
	40	63	22		
	63	100	21		
100	140	19			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at +20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,40		
	30	40	0,40		
40	140	0,42			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,21	Cu : 0,55	
			Mn : 1,50	S : 0,040	
			P : 0,040	N** : 0,012	
	* For nominal thickness > 40 mm C: 0,22. For nominal thickness >100 mm: C content upon agreement				
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/05-CPR-13-1

- 1) Code of the product type: **1.0143**
2) Type: **Sections/Bars S275J0 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	275		
	16	40	265		
	40	63	255		
	63	80	245		
	80	100	235		
	100	140	225		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	410	560	
	100	140	400	540	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	23		
	40	63	22		
	63	100	21		
100	140	19			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
	140	27 at 0°C			
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,40		
	30	40	0,40		
40	140	0,42			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,18	Cu : 0,55	
			Mn : 1,50	S : 0,035	
			P : 0,035	N** : 0,012	
			* For nominal thickness >100 mm: C content upon agreement.		
		** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present			

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/06-CPR-13-1

- 1) Code of the product type: **1.0145**
2) Type: **Sections/Bars S275J2 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	275		
	16	40	265		
	40	63	255		
	63	80	245		
	80	100	235		
	100	140	225		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	410	560	
	100	140	400	540	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	23		
	40	63	22		
	63	100	21		
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at -20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,40		
	30	40	0,40		
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,18	Cu : 0,55	
			Mn : 1,50	S : 0,030	
			P : 0,030		
* For nominal thickness >100 mm: C content upon agreement. Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)					

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/07-CPR-13-1

- 1) Code of the product type: **1.0045**
2) Type: **Sections/Bars S355JR according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
	40	63	335		
	63	80	325		
	80	100	315		
	100	140	295		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	470	630	
	100	140	450	600	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	22		
	40	63	21		
	63	100	20		
100	140	18			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at +20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,45		
	30	40	0,47		
40	140	0,47			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,24	Cu : 0,55	
			Si : 0,55	S : 0,040	
			Mn : 1,60	N** : 0,012	
			P : 0,040		
* For nominal thickness >100 mm: C content upon agreement.					
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/08-CPR-13-1

- 1) Code of the product type: **1.0553**
2) Type: **Sections/Bars S355J0 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
	40	63	335		
	63	80	325		
	80	100	315		
	100	140	295		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	470	630	
	100	140	450	600	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	22		
	40	63	21		
	63	100	20		
100	140	18			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at 0°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,45		
	30	40	0,47		
40	140	0,47			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,20	Cu : 0,55	
			Si : 0,55	S : 0,035	
			Mn : 1,60	N** : 0,012	
			P : 0,035		
			* For nominal thickness > 30 mm C: 0,22. For nominal thickness >100 mm: C content upon agreement		
		** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present			



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/09-CPR-13-1

- 1) Code of the product type: **1.0577**
2) Type: **Sections/Bars S355J2 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
	40	63	335		
	63	80	325		
	80	100	315		
	100	140	295		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	470	630	
	100	140	450	600	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	22		
	40	63	21		
	63	100	20		
100	140	18			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at -20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,45		
	30	40	0,47		
40	140	0,47			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,20	Cu : 0,55	
			Si : 0,55	S : 0,030	
			Mn : 1,60	P : 0,030	
	* For nominal thickness > 30 mm C: 0,22. For nominal thickness >100 mm: C content upon agreement Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)				

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-2/10-CPR-13-1

- 1) Code of the product type: **1.0596**
2) Type: **Sections/Bars S355K2 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
	40	63	335		
	63	80	325		
	80	100	315		
	100	140	295		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	470	630	
	100	140	450	600	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	22		
	40	63	21		
	63	100	20		
100	140	18			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	40 at -20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,45		
	30	40	0,47		
40	140	0,47			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,20	Cu : 0,55	
			Si : 0,55	S : 0,030	
			Mn : 1,60	P : 0,030	
	* For nominal thickness > 30 mm C: 0,22. For nominal thickness >100 mm: C content upon agreement Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)				



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-4/03-CPR-13-1

- 1) Code of the product type: **1.8823**
2) Type: **Sections/Bars S355M according EN 10025-4**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification
Tolerances on dimensions and shape	Angles		EN10056-2	
	I and H sections		EN 10034	
	Tapered Flange I		EN 10024	
	UPE, UPN		EN 10279	
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055	
Yield strength	Nominal thickness (mm)		Values (MPa)	
	>	≤	min	
		16	355	
	16	40	345	
	40	63	335	
	63	80	325	
	80	100	325	
	100	140	320	
Tensile strength	Nominal thickness (mm)		Values (MPa)	
	>	≤	min	max
		40	470	630
	40	63	450	610
	63	80	440	600
	80	100	440	600
	100	140	430	590
	Elongation	Nominal thickness (mm)		Values (%)
>		≤	min	
		140	22	
Impact strength	Nominal thickness (mm)		Values (J)	
	>	≤	min	
		140	40 at -20°C	
Weldability	Nominal thickness (mm)		Values (%)	
	>	≤	max	
		16	0,39	
	16	40	0,39	
	40	63	0,40	
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)	
	>	≤	min	max
		140		C : 0,16 Mn : 1,60 Si : 0,50 P : 0,035 S : 0,030 Nb : 0,05 V : 0,10
				Ti : 0,05 Cr : 0,30 Mo : 0,10 Ni : 0,50 Cu : 0,55 N : 0,015
			Al* : 0,02	
* If sufficient other nitrogen binding elements are present, the minimum aluminium requirement does not apply				

EN 10025-1:2004



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-5/01-CPR-13-1

- 1) Code of the product type: **1.8959**
 2) Type: **Sections/Bars S355J0W according EN 10025-5**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
 Vratimovska 689
 70702 Ostrava Kuncice
 Czech Republic
 Tel. +420 59 733 1111
 www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
 System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
 Director of Rolling Mills

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≠3	40	470	630	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≠3	40	22		
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		40	27 at 0°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	NPD		
		16			
	16	40			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	min	max	
		40	C : 0,16	S : 0,040	
			Si : 0,50	N* : 0,009	
			P : 0,040		
		Mn : 0,50	Mn : 1,50		
		Cu : 0,25	Cu : 0,55		
		Cr : 0,40	Cr : 0,80		
* It is permissible to exceed the specified values provided that for each increase of 0,001 % N, the Pmax content will be reduced by 0,005%; the N content of the ladle analysis, however, shall not be more than 0,012%. The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present. The N binding elements shall be mentioned in the inspection document.					
The steels may show a Ni content of max. 0,65%. The steels may contain max. 0,30% Mo and max. 0,15% Zr.					

Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-5/02-CPR-13-1

- 1) Code of the product type: **1.8965**
2) Type: **Sections/Bars S355J2W according EN 10025-5**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorrňák
Director of Rolling Mills



Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≠3	40	470	630	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≠3	40	22		
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		40	27 at -20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	NPD		
		16			
	16	40			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	min	max	
		40	C : 0,16	S : 0,035	
			Si : 0,50	N* : 0,009	
			P : 0,035		
		Mn : 0,50	Mn : 1,50		
		Cu : 0,25	Cu : 0,55		
		Cr : 0,40	Cr : 0,80		
* It is permissible to exceed the specified values provided that for each increase of 0,001 % N, the Pmax content will be reduced by 0,005%; the N content of the ladle analysis, however, shall not be more than 0,012%. The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present.					
Addition of nitrogen binding elements: the steels shall contain at least one of the following elements: Al total ≥ 0,020%, Nb: 0,015 - 0,060%, V: 0,02-0,12%, Ti: 0,02 - 0,10%. If these elements are used in combination, at least one of them shall be present with the minimum content indicated.					
The steels may show a Ni content of max. 0,65%. The steels may contain max. 0,30% Mo and max. 0,15% Zr.					
Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)					



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMOS-5/03-CPR-13-1

- 1) Code of the product type: **1.8967**
2) Type: **Sections/Bars S355K2W according EN 10025-5**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Ostrava a.s.
Vratimovska 689
70702 Ostrava Kuncice
Czech Republic
Tel. +420 59 733 1111
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1020 Technical and Test Institute for Construction Prague (TZUS) performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificates of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Alan Dorňák
Director of Rolling Mills

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≠3	40	470	630	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≠3	40	22		
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		40	40 at -20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	NPD		
		16			
	16	40			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	min	max	
		40	C : 0,16	S : 0,035	
			Si : 0,50	N* : 0,009	
			P : 0,035		
		Mn : 0,50	Mn : 1,50		
		Cu : 0,25	Cu : 0,55		
		Cr : 0,40	Cr : 0,80		
* It is permissible to exceed the specified values provided that for each increase of 0,001 % N, the Pmax content will be reduced by 0,005%; the N content of the ladle analysis, however, shall not be more than 0,012%. The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present.					
Addition of nitrogen binding elements: the steels shall contain at least one of the following elements: Al total ≥ 0,020%, Nb: 0,015 - 0,060%, V: 0,02-0,12%, Ti: 0,02 - 0,10%. If these elements are used in combination, at least one of them shall be present with the minimum content indicated.					
The steels may show a Ni content of max. 0,65%. The steels may contain max. 0,30% Mo and max. 0,15% Zr.					
Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)					